

## TECHNICAL DATA SHEET

DESCRIPTION: Jar Unique 50ml con Cuvette Sple.

TECHNICAL SHEET: E196/900 REV. 7

DATE: 21/04/2022

DRAW: E196/900-04

MATERIAL: See the Components section

CUSTOMER:

ITEM:

## COMPONENTS

DRAW NUMBER	PRODUCT DESCRIPTION	MATERIAL	COLOR
B207/110	Bush 50ML PP	PP	Neutral
1/3018/0	Jar Unique Glass Sple. Sede Bussola	Glass	Neutral

## PACKING LIST

DESCRIPTION	CODE	SPECIFICATIONS	CRT. PCS.	CRT. WT. (KG)	PIECES PALLET	PALLET DIMENSIONS
Others	A	STD	20	3,300	2.240	800x1200x1000
Cardboard Box - Tray With Honeycomb	B	CUSTOM	60	9,738	1.440	800x1200x970
Others	C	Per verniciatura matte	20	3,300	2.240	800x1200x1000
Cardboard Box - Tray With Honeycomb	D	CUSTOM per venice matte	60	9,738	1.440	800x1200x970

## VARIABLES

REF.	DESCRIPTION	QUOTA	+	-	UNIT	AQL
1	Total height	59,3	0,8	0,8	mm	1.5
2	Neck height	15,7	0,45	0,45	mm	0.65
A	External Ø	66,9	0,8	0,6	mm	1.5
E	Ø of thread's base	59,8	0,4	0,4	mm	0.65
I	Inner Ø on 1mm depth	43,8	0,3	0,3	mm	0.65
T	Thread crest Ø	62,0	0,4	0,4	mm	0.65
TEST1	Weight	150,0	2,0	2,0	g	1.5
TEST2	Total capacity size	61,0	2,0	2,0	ml	0.65
TEST3	Vacuum check	0,0	0,0	0,0	-	0.65

&gt; Ref.TEST2: The test has to made with the cover DE LUXE 66 produced by Lumson.

&gt; Ref. TEST3: The test must be done with the cover DE LUXE 66 Sple. PETG+AL and

cover Slim 66 Sple. PETG. produced by Lumson.

## ATTRIBUTES

REF.	DESCRIPTION	AQL	INSTRUMENT	INSTRUCTIONS
D.006.001.001	Not correspondence with the order	0.01	-	-
D.046.001.001	External dirt/inclusion minor	4	-	-

## TECHNICAL DATA SHEET

REF.	DESCRIPTION	AQL	INSTRUMENT	INSTRUCTIONS
D.047.001.001	External dirt/inclusion major	1.5	-	-
D.048.001.001	Internal dirt (foreign object)	0.65	-	-
D.049.001.001	Bubbles major	1.5	-	-
D.050.001.001	Bubbles minor	4	-	-
D.005.004.001	Cut, holes, cracks, breaks	0.65	-	-
D.005.009.001	Major defect of not homogeneous glass distribution on the bottom/body	1.5	-	-
D.005.009.002	Minor defect of not homogeneous glass distribution on the bottom/body	4	-	-
D.011.001.001	Not consistent thread orientation	0.65	-	-
D.012.002.004	Residues of frosting process (acid, water)	0.65	-	-
D.012.002.005	Chipped glass	0.01	-	-
D.012.002.006	Sharp wings	0.01	-	-
D.026.001.001	Sharp flash / breaks	0.01	-	-
D.012.002.008	Sticked bottles	0.01	-	-
D.012.002.010	Bird swings	0.01	-	-
D.012.004.001	Shear marks on the body	4	-	-
D.012.004.002	Fold on the mould	0.65	-	-
D.012.004.004	Clearly visible fold >20mm	1.5	-	-
D.012.004.005	Shallow fold > 10mm and < 20mm	4	-	-
D.012.004.006	Marked surface with evident arcs, hammering, peel of orange, undulations, curlings, scorches	1.5	-	-
D.012.004.007	Marked surface with not evident arcs, hammering, peel of orange, undulations, curlings, scorches	4	-	-
D.012.004.020	Major absence of frosting	1.5	-	-
D.012.004.021	Minor absence of frosting	4	-	-
D.007.002.001	Colour not consistent with colourboard/BAT	4	-	-
D.007.002.002	Not uniform colour	4	-	-
D.004.005.002	Not consistent decoration resistance according to IDT.LMS.041	0.65	-	-
D.004.003.005	Not consistent positioning of the decoration	0.65	-	-
D.004.002.008	Partially missing or not readable legal texts	0.65	-	-
D.004.002.001	Major decoration defects (missing parts, smears, foil defects, residues of decoration)	1.5	-	-
D.004.002.005	Minor decoration defects (missing parts, smears, foil defects, residues of decoration)	4	-	-
D.004.002.003	Clearly visible missing parts of decoration on logo, customer's name	0.65	-	-
D.003.006.013	Major lacquering/metallisation defects (dots, strainings, peel of orange, lacks)	1.5	-	-
D.003.006.014	Minor lacquering/metallisation defects (dots, strainings, peel of orange, lacks)	4	-	-
D.004.008.007	Not uniform distribution of lacquering/metallization	4	-	-
D.004.002.011	Absence of major parts of metallization/lacquering	1.5	-	-
D.004.002.012	Absence of minor parts of metallization/lacquering	4	-	-
D.013.001.001	Mixing up with different articles	0.01	-	-
D.006.001.002	Not consistent label of the secondary packagin	0.01	-	-
D.014.001.001	Secondary packing different than the ordered one	1.5	-	-
D.006.001.003	Integrity and cleanliness of the secondary packing	0.65	-	-

In the sales configuration VBO glass or VBO glass with the following patterns

(screen printing and/or hot stamping), the presence of fine dust between glass

and couvettes is not excluded (see representative image attached), respecting

however the sale specifications.